

www.prolightopto.com





ProLight PK2N-4LxE-SSD 4W Power LED Technical Datasheet Version: 2.1

ProLight Opto PK2N Series

Features

- · Best thermal material solution of the world
- · Best Moisture Sensitivity: JEDEC Level 1
- · RoHS compliant

Main Applications

- \cdot Entertainment Lighting
- \cdot Commercial Lighting
- \cdot Indoor Lighting
- · Outdoor Lighting


Introduction

•ProLight Phenix 3535, is one of the smallest high power LED footprint available by ProLight Opto, has offered extended solid-state lighting design possibilities. ProLight Phenix 3535 is designed with ProLight own Patents and using copper leadframe, the best thermal material of the world.

•Phenix 3535 qualifies as the JEDEC Level 1 MSL sensitivity level and suitable for SMD process, Pb_free reflow soldering capability, and full compliance with EU Reduction of Hazardous Substances (RoHS) legislation.



Emitter Mechanical Dimensions



Circuit Diagram (G,B,D) Anode(+) O Cathode(-) Anode(+) O Cathode(-) O Slug Slug O

Notes:

- 1. The cathode side of the device is denoted by the chamfer on the part body.
- 2. Electrical insulation between the case and the board is required. Do not electrically connect either the anode or cathode to the slug.
- 3. Drawing not to scale.
- 4. All dimensions are in millimeters.
- 5. Unless otherwise indicated, tolerances are \pm 0.1mm.
- 6. Please do not solder the emitter by manual hand soldering, otherwise it will damage the emitter.
- 7. Please do not use a force of over 0.3kgf impact or pressure on the lens of the LED, otherwise it will cause a catastrophic failure.

*The appearance and specifications of the product may be modified for improvement without notice.



Flux Characteristics, $T_J = 25^{\circ}C$

		Luminous Flux or Power					
Color	Part Number Emitter	@350mA		Refer @700mA	Refer @1000mA		
	Emitter	Minimum	Typical	Typical	Typical		
Red	PK2N-4LRE-SSD	40 lm	75 lm	144 lm	194 lm		
Green	PK2N-4LGE-SSD	110 lm	140 lm	224 lm	281 lm		
Blue	PK2N-4LBE-SSD	23.5 lm	26 lm	47 lm	64 lm		
Royal Blue	PK2N-4LDE-SSD	560 mW	640 mW	1160 mW	1570 mW		

• ProLight maintains a tolerance of ± 7% on flux and power measurements.

• Please do not drive at rated current more than 1 second without proper heat sink.

Electrical Characteristics, T_J = 25°C

Forward Voltage V _F (V)						Thermal
		@350mA		Refer @700mA	Refer @1000mA	Resistance Junction to Slug
Color	Min.	Тур.	Max.	Тур.	Тур.	(°C/W)
Red	1.80	2.20	2.60	2.41	2.57	7
Green	2.50	2.70	3.70	2.95	3.13	7
Blue	2.70	2.95	3.30	3.11	3.22	7
Royal Blue	2.70	2.95	3.30	3.11	3.22	7

• ProLight maintains a tolerance of $\pm 0.1V$ for Voltage measurements.

Optical Characteristics at 350mA, $T_J = 25^{\circ}C$

Radiation	Color	Domi	nant Wavelen	gth λ_D	Total included Angle (degrees)	Viewing Angle (degrees)
Pattern	Color	Min.	Тур.	Max.	θ _{0.90V}	2 θ _{1/2}
	Red	610 nm	625 nm	630 nm	160	130
Lambartian	Green	525 nm	530 nm	535 nm	160	130
Lambertian	Blue	455 nm	465 nm	475 nm	160	130
	Royal Blue	450 nm	455 nm	460 nm	160	130

• ProLight maintains a tolerance of ± 1nm for dominant wavelength measurements.



Absolute Maximum Ratings

Parameter	Red/Green/Blue/Royal Blue
DC Forward Current (mA)	1000
Peak Pulsed Forward Current (mA)	1200 (less than 1/10 duty cycle@1KHz)
ESD Sensitivity	+4000\/ (Class III)
(HBM per MIL-STD-883E Method 3015.7)	±4000V (Class III)
LED Junction Temperature	120°C
Operating Board Temperature	-40°C - 90°C
at Maximum DC Forward Current	-40 C - 30 C
Storage Temperature	-40°C - 120°C
Soldering Temperature	JEDEC 020c 260°C
Allowable Reflow Cycles	3
Reverse Voltage	Not designed to be driven in reverse bias



Radiometric Power Bin Structure at 350mA

	Color	Bin Code	Minimum Radiometric Power (mW)	Maximum Radiometric Power (mW)	Available Color Bins
		R	560	610	All
	Royal Blue	S	610	660	All
		Т	660	710	【1】

 \bullet ProLight maintains a tolerance of \pm 7% on flux and power measurements.

• The flux bin of the product may be modified for improvement without notice.

• ^[1] The rest of color bins are not 100% ready for order currently. Please ask for quote and order possibility.

Photometric Luminous Flux Bin Structure at 350mA

Color	Bin Code	Minimum Photometric Flux (Im)	Maximum Photometric Flux (Im)	Available Color Bins
	R	40	50	[1]
	S1	50	60	[1]
	S2	60	70	4,6 ^[1]
Red	T1	70	80	4,6 ^[1] 4,6 ^[1]
	T2	80	90	2 ^[1]
	U1	90	100	【1】
	U2	100	110	[1]
	V1	110	120	[1]
0	V2	120	130	【1】
Green	W1	130	140	All
	W2	140	150	[1]
	Р	23.5	30.6	1,2 ^[1]
Blue	Q	30.6	39.8	[1]
	R	39.8	51.7	[1]

 \bullet ProLight maintains a tolerance of \pm 7% on flux and power measurements.

• The flux bin of the product may be modified for improvement without notice.

• ^[1] The rest of color bins are not 100% ready for order currently. Please ask for quote and order possibility.



Dominant Wavelength Bin Structure

Color	Bin Code	Minimum Dominant Wavelength (nm)	Maximum Dominant Wavelength (nm)
	2	610	620
Red	4	620	625
	6	625	630
	2	525	530
Green	3	530	535
	A	455	460
Dhuo	1	460	465
Blue	2	465	470
	3	470	475
	5	450	455
Royal Blue	6	455	460

• ProLight maintains a tolerance of \pm 1nm for dominant wavelength measurements.

Note: Although several bins are outlined, product availability in a particular bin varies by production run and by product performance. Not all bins are available in all colors.

Color	Bin Code	Minimum Voltage (V)	Maximum Voltage (V)
	A	1.8	2.0
Red	В	2.0	2.2
Reu	D	2.2	2.4
	E	2.4	2.6
	а	2.5	2.7
	А	2.7	2.9
Croon	В	2.9	3.1
Green	D	3.1	3.3
	E	3.3	3.5
	F	3.5	3.7
	А	2.7	2.9
Blue	В	2.9	3.1
	D	3.1	3.3
	A	2.7	2.9
loyal Blue	В	2.9	3.1
	D	3.1	3.3

Forward Voltage Bin Structure


• ProLight maintains a tolerance of \pm 0.1V for Voltage measurements.

Note: Although several bins are outlined, product availability in a particular bin varies by production run and by product performance. Not all bins are available in all colors.




Color Spectrum, T_J = 25°C

1. Royal Blue > Blue > Green > Red



Junction Temperature Relative Characteristics

1. Junction Temperature vs. Relative Light Output at 350mA





2024/07 | DS-1177



Forward Current Characteristics, T_J = 25°C

1. Forward Voltage vs. Forward Current







2024/07 | DS-1177



Forward Current Characteristics, $T_1 = 25^{\circ}C$


2. Forward Current vs. Normalized Relative Luminous Flux







Typical Representative Spatial Radiation Pattern





Moisture Sensitivity Level - JEDEC Level 1

			Soak Requirements				
Level	/el Floor Life		Standard		Accelerated Environment		
	Time	Conditions	Time (hours)	Conditions	Time (hours)	Conditions	
1	Unlimited	≤30°C / 85% RH	168 +5/-0	85°C / 85% RH	NA	NA	

- The standard soak time includes a default value of 24 hours for semiconductor manufature's exposure time (MET) between bake and bag and includes the maximum time allowed out of the bag at the distributor's facility.
- Table below presents the moisture sensitivity level definitions per IPC/JEDEC's J-STD-020C.

	Soak Requirements					
Level	Floor	Floor Life		Standard		Environment
	Time	Conditions	Time (hours)	Conditions	Time (hours)	Conditions
1	Unlimited	≤30°C / 85% RH	168 +5/-0	85°C / 85% RH	NA	NA
2	1 year	≤30°C / 60% RH	168 +5/-0	85°C / 60% RH	NA	NA
2a	4 weeks	≤30°C / 60% RH	696 +5/-0	30°C / 60% RH	120 +1/-0	60°C / 60% RH
3	168 hours	≤30°C / 60% RH	192 +5/-0	30°C / 60% RH	40 +1/-0	60°C / 60% RH
4	72 hours	≤30°C / 60% RH	96 +2/-0	30°C / 60% RH	20 +0.5/-0	60°C / 60% RH
5	48 hours	≤30°C / 60% RH	72 +2/-0	30°C / 60% RH	15 +0.5/-0	60°C / 60% RH
5a	24 hours	≤30°C / 60% RH	48 +2/-0	30°C / 60% RH	10 +0.5/-0	60°C / 60% RH
6	Time on Label (TOL)	≤30°C / 60% RH	Time on Label (TOL)	30°C / 60% RH	NA	NA



Qualification Reliability Testing

Stress Test	Stress Conditions	Stress Duration	Failure Criteria
Room Temperature Operating Life (RTOL)	25°C, I _F = max DC (Note 1)	1000 hours	Note 2
Wet High Temperature Operating Life (WHTOL)	85°C/60%RH, I _F = max DC (Note 1)	1000 hours	Note 2
Wet High Temperature Storage Life (WHTSL)	85°C/85%RH, non-operating	1000 hours	Note 2
High Temperature Storage Life (HTSL)	110°C, non-operating	1000 hours	Note 2
Low Temperature Storage Life (LTSL)	-40°C, non-operating	1000 hours	Note 2
Non-operating Temperature Cycle (TMCL)	-40°C to 120°C, 30 min. dwell, <5 min. transfer	200 cycles	Note 2
Mechanical Shock	1500 G, 0.5 msec. pulse, 5 shocks each 6 axis		Note 3
Natural Drop	On concrete from 1.2 m, 3X		Note 3
Variable Vibration Frequency	10-2000-10 Hz, log or linear sweep rate, 20 G about 1 min., 1.5 mm, 3X/axis		Note 3
Solder Heat Resistance (SHR)	260°C ± 5°C, 10 sec.		Note 3
Solderability	Steam age for 16 hrs., then solder dip at 260°C for 5 sec.		Solder coverage on lead

Notes:

1. Depending on the maximum derating curve.

2. Criteria for judging failure

Item	Test Condition	Criteria for Judgement		
liem		Min.	Max.	
Forward Voltage (V _F)	I _F = max DC		Initial Level x 1.1	
Luminous Flux or Radiometric Power (Φ_V)	I _F = max DC	Initial Level x 0.7		
Reverse Current (I _R)	$V_R = 5V$		50 µA	


* The test is performed after the LED is cooled down to the room temperature.

3. A failure is an LED that is open or shorted.



Recommended Solder Pad Design

Standard Emitter




- All dimensions are in millimeters.
- Electrical isolation is required between Slug and Solder Pad.



Reflow Soldering Condition


Profile Feature	Sn-Pb Eutectic Assembly	Pb-Free Assembly
Average Ramp-Up Rate	3°C / second max.	3°C / second max.
(T _{Smax} to T _P)		
Preheat		
– Temperature Min (T _{Smin})	100°C	150°C
– Temperature Max (T _{Smax})	150°C	200°C
– Time (t _{smin} to t _{smax})	60-120 seconds	60-180 seconds
Time maintained above:		
– Temperature (T _L)	183°C	217°C
– Time (t _i)	60-150 seconds	60-150 seconds
Peak/Classification Temperature (T _P)	240°C	260°C
Time Within 5°C of Actual Peak	10-30 seconds	20-40 seconds
Temperature (t _p)		
Ramp-Down Rate	6°C/second max.	6°C/second max.
Time 25°C to Peak Temperature	6 minutes max.	8 minutes max.



- We recommend using the M705-S101-S4 solder paste from SMIC (Senju Metal Industry Co., Ltd.) for lead-free soldering.
- Do not use solder pastes with post reflow flux residue>47%. (58Bi-42Sn eutectic alloy, etc) This kind of solder pastes may cause a reliability problem to LED.
- All temperatures refer to topside of the package, measured on the package body surface.
- Repairing should not be done after the LEDs have been soldered. When repairing is unavoidable, a double-head soldering iron should be used. It should be confirmed beforehand whether the characteristics of the LEDs will or will not be damaged by repairing.
- Reflow soldering should not be done more than three times.
- When soldering, do not put stress on the LEDs during heating.
- After soldering, do not warp the circuit board.



Emitter Reel Packaging




Notes:

- 1. Drawing not to scale.
- 2. All dimensions are in millimeters.
- 3. Unless otherwise indicated, tolerances are $\pm\,0.1\text{mm}.$



Emitter Reel Packaging



Notes:

- 1. Empty component pockets sealed with top cover tape.
- 2. 1000 pieces per reel.
- 3. Drawing not to scale.
- 4. All dimensions are in millimeters.



Precaution for Use

Storage

Please do not open the moisture barrier bag (MBB) more than one week. This may cause the leads of LED discoloration. We recommend storing ProLight's LEDs in a dry box after opening the MBB. The recommended storage conditions are temperature 5 to 30 °C and humidity less than 40% RH. It is also recommended to return the LEDs to the MBB and to reseal the MBB.


- The slug is is not electrically neutral. Therefore, we recommend to isolate the heat sink.
- We recommend using the M705-S101-S4 solder paste from SMIC (Senju Metal Industry Co., Ltd.) for lead-free soldering.
- Do not use solder pastes with post reflow flux residue>47%. (58Bi-42Sn eutectic alloy, etc) This kind of solder pastes may cause a reliability problem to LED.
- Any mechanical force or any excess vibration shall not be accepted to apply during cooling process to normal temperature after soldering.
- Please avoid rapid cooling after soldering.
- Components should not be mounted on warped direction of PCB.
- Repairing should not be done after the LEDs have been soldered. When repairing is unavoidable, a heat plate should be used. It should be confirmed beforehand whether the characteristics of the LEDs will or will not be damaged by repairing.
- This device should not be used in any type of fluid such as water, oil, organic solvent and etc. When cleaning is required, isopropyl alcohol should be used.
- When the LEDs are illuminating, operating current should be decide after considering the package maximum temperature.
- The appearance, specifications and flux bin of the product may be modified for improvement without notice. Please refer to the below website for the latest datasheets. <u>http://www.prolightopto.com/</u>

Handling of Silicone Lens LEDs

Notes for handling of silicone lens LEDs

- Please do not use a force of over 0.3kgf impact or pressure on the silicone lens, otherwise it will cause a catastrophic failure.
- The LEDs should only be picked up by making contact with the sides of the LED body.
- Avoid touching the silicone lens especially by sharp tools such as Tweezers.
- Avoid leaving fingerprints on the silicone lens.
- Please store the LEDs away from dusty areas or seal the product against dust.
- When populating boards in SMT production, there are basically no restrictions regarding the form of the pick and place nozzle, except that mechanical pressure on the silicone lens must be prevented.
- Please do not mold over the silicone lens with another resin. (epoxy, urethane, etc)





2024/07 | DS-1177



Disclaimers

ProLightopto Technology has made every reasonable effort to ensure the accuracy of the information in this datasheet. However, it should be understood that this information is for guidance only and does not constitute any offer or part of a contract.

ProLightopto Technology does not guarantee or accept any legal liability for the accuracy, completeness, or usefulness of any information, product, technology, or process disclosed in this datasheet. The company reserves the right to make changes or improvements to this datasheet at its discretion.

Unless this datasheet is incorporated into a formal contract, customers should not rely on the information as a binding commitment to any specifications or product parameters by ProLightopto Technology. Customers are advised to verify that the information is current and complete before entering into any contract or acknowledging any purchase order. Therefore, all products described herein are subject to ProLightopto Technology's terms and conditions at the time of order acknowledgment.

Unless agreed upon by contractual agreement, not all parameters of each product are necessarily tested. ProLightopto Technology does not warrant or grant any license, either expressed or implied, under its patent rights or the rights of others.

Reproduction of the information contained herein is permitted only if done without any modifications or alterations. Altering this information and reproducing it is considered an unfair and deceptive business practice. ProLightopto Technology is not responsible or liable for any such altered documentation.

Reselling ProLightopto Technology's products with statements that differ from or exceed the parameters specified by ProLightopto Technology voids all express or implied warranties for the associated product or service and is considered an unfair and deceptive business practice. ProLightopto Technology is not responsible or liable for any such statements.

ProLightopto Technology's products are not authorized for use as critical components in life support devices or systems without explicit written approval from ProLightopto Technology.

For the purposes of this disclaimer :

- 1. Life support devices or systems are defined as those intended for surgical implant into the body or those that support or sustain life. Their failure, when used according to instructions for use provided in the labeling, can reasonably be expected to result in significant injury to the user.
- 2. A critical component is any component of a life support device or system whose failure can reasonably be expected to cause the failure of the device or system, or to affect its safety or effectiveness.